

SILICONE SEALANT



-55°C ÷ +180°C

FUNCTIONAL CURING TIME

3 - 6 hours

MAXIMUM THICKNESS

0,60 - 3 mm

TENSILE STRENGTH (N/MM2)

1,8 - 3

FEATURES

One component moisture silicone based sealant and adhesive releasing non corrosive and odourless by-products. Provides an extremely flexible gasket between surfaces made of various materials (metals, pastics, glass, ceramics, ecc.). Suitable for sealing gear boxes, pumps and motors flanges, oil and water containers, and air forced pipes. Resistant to vibrations, thermal shocks, pressurized air, water, gas, LPG, oil and several chemicals. Keeps its sealing properties within temperatures of -55°C and +180°C. Sealed parts can be disassembled using normal tools.



Products in compliance with the directive 2002/95/EC

RoHS2

Products in compliance with the directive 2011/65/EU

LOX5920



Highly oil resistant, transparent, silicone sealant

CODE	CONTAINER
LOX5920	310 ML

